



Continuous casting aluminium alloys.

Standard: **UNI EN 1676 and 1706**

Alloy group: **Al Si 7 Mg**

Alloy designation: **EN AB and AC 42200 Al Si 7 Mg 0.6**

Replaces:

CHEMICAL COMPOSITION %

ALLOY		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Individual impurities	Global impurities
EN AB 42200	min	6,5				0,50						0,10		
	max	7,5	0,15	0,03	0,10	0,70	-	-	0,07	-	-	0,18	0,03	0,10
	min	6,5				0,50						0,10		
	max	7,5	0,15	0,02	0,05	0,70	-	-	0,07	-	-	0,20	0,03	0,10

MECHANICAL FEATURES DETECTED FROM SEPARATE CASTING TEST SPECIMENS

Casting process	Temper designations	Rm Tensile strenght		Sp 0,2 Yield strenght		A Elongation		HB Brinell hardness	
		EN 1706		EN 1706		EN 1706		EN 1706	
		Mpa	N/mm2	Mpa	N/mm2	%	%	HBW	HB
SAND (as cast)			-		-		-		-
Hardened and Aged artif.	T6	250	250 - 320	210	220 - 280	1	1 - 2	85	90 - 110
SHELL (as cast)			-		-		-		-
Partially Aged	T64	290	290 - 320	210	210 - 240	3	6 - 8	90	90 - 100
Hardened and Aged artif.	T6	320	300 - 350	240	240 - 280	6	4 - 6	100	100 - 115
PRESSURE DIE (as cast)									

PHYSICAL PROPERTIES (indicative values subject to the UNI EN and ex DIN Standards)

DENSITY	2.66 Kg/dm ³	THERMAL CONDUCTIVITY at 20°C	150 - 180 W/(m K)
MELTING RANGE or MELTING POINT	550 °C	LINEAR THERMAL EXPANSION from 20 t 100°C	-
	625 °C	LINEAR THERMAL EXPANSION from 20 t 200°C	22.0-10-6/°C
SPECIFIC HEAT (at 100)°	0.92 J/Gk	LINEAR THERMAL EXPANSION from 20 t 300°C	-
LINEAR SHRINKAGE IN SAND PROCESS	1.1 - 1.2 %	SUGGESTED MAXIMUM TEMPERATURE	780 °C
LINEAR SHRINKAGE IN SHELL PROCESS	0.8 - 1.1 %	SUGGESTED CASTING TEMPERATURE	
ELECTRIC CONDUCTIVITY	20 - 26 MS/m	^o in sand	680 - 750 °C
MODULUS OF ELASTICITY	7400 Kg/mm ²	^o in shell	680 - 750 °C
		^o in pressure die	-

TECHNOLICICL FEATURES, QUALITATIVE INDICATIONS

MECHANICAL RESISTANCE WHEN HOT	MEDIUM
GENERAL RESIATANCE TO CORROSION	GOOD
MACHINABILITY	GOOD
CASTABILITY	GOOD
POLISHING	GOOD

RESISTANCE TO SHRINKAGE CRACKING	SMALL
PRESSURE SEALING	GOOD
WELDABILITY	GOOD
SUITABILITY FOR DECORATIVE ANODISING	LOW
SUITABILITY FOR PROTECTIVE ANODISING	

Address: Veliköy Sanayi Bölgesi 1. Kısım Osman Uzun Cad. No: 2/1 Çerkezköy / Tekirdağ / TURKEY
Email: info@bayrammetal.com.tr - **Phone:** +90 282 746 10 41 (Pbx) - **Web:** bayrammetal.com.tr