



Continuous casting aluminium alloys.

Standard: **UNI EN 1676 and 1706**

Alloy group: **Al Si**

Alloy designation: **EN AB and AC 44300 Al Si 12 (Fe)(a)**

Replaces: **DIN 230 D GD Al Si 12**

CHEMICAL COMPOSITION %

ALLOY		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Individual impurities	Global impurities
EN AB 44300	min	10,5	0,45											
	max	13,5	0,90	0,08	0,55	-	-	-	0,15	-	-	0,15	0,05	0,25
DIN 230 D - GD Al Si 12	min	10,5												
	max	13,5	1,00	0,10	0,4	-	-	-	0,15	-	-	0,15	0,05	0,25

MECHANICAL FEATURES DETECTED FROM SEPARATE CASTING TEST SPECIMENS

Casting process	Temper designations	Rm Tensile strenght		Sp 0,2 Yield strenght		A Elongation		HB Brinell hardness	
		EN 1706	DIN 1725	EN 1706	DIN 1725	EN 1706	DIN 1725	EN 1706	DIN 1725
		Mpa	N/mm2	Mpa	N/mm2	%	%	HBW	HB
SAND (as cast)			-		-		-		-
			-		-		-		-
SHELL (as cast)			-		-		-		-
			-		-		-		-
PRESSURE DIE (as cast)	F	240	220 - 280	130	140 - 180	1	1 - 3	60	60 - 100

PHYSICAL PROPERTIES (indicative values subject to the UNI EN and ex DIN Standards)

DENSITY	2.68 Kg/dm ³
MELTING RANGE or MELTING POINT	570 °C 580 °C
SPECIFIC HEAT (at 100)°	0.90 J/Gk
LATENT HEAT OF MELTING	
LINEAR SHRINKAGE IN HIGH PRESSURE	0.4 - 0.6 %
ELECTRIC CONDUCTIVITY	16 - 22 MS/m
MODULUS OF ELASTICITY	7500 Kg/mm ²

THERMAL CONDUCTIVITY at 20°C	130 - 160 W/(m K)
LINEAR THERMAL EXPANSION from 20 t 100°C	20 10-6/°K
LINEAR THERMAL EXPANSION from 20 t 200°C	21-10-6/K
LINEAR THERMAL EXPANSION from 20 t 300°C	-
SUGGESTED MAXIMUM TEMPERATURE	740 °C
SUGGESTED CASTING TEMPERATURE	
^o in sand	-
^o in shell	-
^o in pressure die	640 - 680

TECHNOLOGICAL FEATURES, QUALITATIVE INDICATIONS

STRENGTH AT ELEVATED TEMPERATURE(to 200°C)	MEDIUM
GENERAL RESISTANCE TO CORROSION	GOOD
MACHINABILITY	MEDIUM
CASTABILITY	EXCELLENT
POLISHING	MEDIUM

RESISTANCE TO HOT TEARING	SMALL
PRESSURE TIGHTNESS	MEDIUM
WELDABILITY	MEDIUM
DECORATIVE ANODISING	LOW
PROTECTIVE ANODISING	

Address: Veliköy Sanayi Bölgesi 1. Kısım Osman Uzun Cad. No: 2/1 Çerkezköy / Tekirdağ / TURKEY
Email: info@bayrammetal.com.tr - **Phone:** +90 282 746 10 41 (Pbx) - **Web:** bayrammetal.com.tr